

Product Data Sheet

Nemcon™ H PC DP105/X3 BK

Nemcon™ H-series products are designed for use in high performance electronic assemblies where heat removal is critical to system performance. Nemcon™ H PC DP105/X3 BK is a black colored, thermally conductive polycarbonate compound, combining excellent thermal conductivity with high HDT and good processability.

Typical Applications

- Housings for power components.
- Encapsulation/housings for bobbins, actuators, and coils.
- IC thermal management components, such as heat sinks, heat spreaders, or heat pipes.
- LED lighting assemblies.

Properties*	Standard	Unit	Typical Value
Physical			
Specific Gravity	D 792	-	1.45
Mechanical			
Tensile Stress @ brk, 50 mm/min	D 638	MPa.	59
Tensile Strain @ brk, 50 mm/min	D 638	%	1.6
Tensile Modulus, 50 mm/min	D 638	MPa.	6900
Flexural Stress @ brk, 1.3 mm/min, 50 mm span	D 790	MPa.	85
Flexural Modulus, 1.3 mm/min, 50 mm span	D 790	MPa.	8200
Izod Impact, notched @ 23°C	D 256	ft-lb/in.	0.6
Thermal			
HDT @ 264 psi, 3.2 mm, unannealed	D 648	°C	136
Conductivity			
Thermal Conductivity	E 1461	W/mK	6.10
Electrical - Surface Resistivity	D 257	Ohms/sq.	8.0E+12

*All properties are measured after 48 hours of conditioning at 23°C and 50% relative humidity. All samples are prepared according to ASTM standards. Variations within normal tolerances are possible for various types of colors and functional properties like UV resistance.

Technical information contained in this report is furnished without cost or obligation. Nothing contained in this bulletin shall be considered a recommendation for use which may infringe on any patent rights or as an endorsement of any material supplied by Ovation Polymers, Inc. (OPTEM). Since Ovation Polymers, Inc. has no control over the many different conditions under which this information and our products may be used, Ovation Polymers, Inc. recommends each user to conduct its own tests to determine a material's suitability for a particular use. We do not guarantee the applicability or suitability of our products in any given situation. The properties listed herein fall within the normal range of product properties and should not be used to establish specification limits. Colorants, additives and secondary operations of any kind may alter some or all of the properties of these materials. Flammability information included herein indicates only the potential for meeting UL listing criteria and does not necessarily mean that UL listings for any given material have been secured.