

## Product Data Sheet

### UTTAP™ – QU HT530 GF

Glass reinforced (30 %) - High Temperature Polyamide Alloy, excellent chemical and electrical resistance, high stiffness, modulus and HDT.

Properties*	Standard	Unit	Typical Value
<b>Physical</b>			
Specific Gravity	D 792		1.48
Water Absorption, 24 hours	D 570	%	0.80
<b>Mechanical</b>			
Tensile Stress @ yld, 50 mm/min	D 638	MPa.	160
Tensile Strain @ brk, 50 mm/min	D 638	%	3.5
Tensile Modulus, 50 mm/min	D 638	MPa.	6000
Flexural Stress @ yld, 1.3 mm/min, 50 mm span	D 790	MPa.	205
Flexural Modulus, 1.3 mm/min, 50 mm span	D 790	MPa.	10500
Izod Impact, notched @ 23°C	D 256	J/m	70
<b>Thermal</b>			
HDT @ 66 psi, 3.2 mm, unannealed	D 648	°C	220
HDT @ 264 psi, 3.2 mm, unannealed	D 648	°C	218

\*All properties are measured after 48 hours of conditioning at 23°C and 50% relative humidity. All samples are prepared according to ASTM standards. Variations within normal tolerances are possible for various types of colors and functional properties like UV resistance.

Technical information contained in this report is furnished without cost or obligation. Nothing contained in this bulletin shall be considered a recommendation for use which may infringe on any patent rights or as an endorsement of any material supplied by Ovation Polymers, Inc. (OPTeM). Since Ovation Polymers, Inc. has no control over the many different conditions under which this information and our products may be used, Ovation Polymers, Inc. recommends each user to conduct its own tests to determine a material's suitability for a particular use. We do not guarantee the applicability or suitability of our products in any given situation. The properties listed herein fall within the normal range of product properties and should not be used to establish specification limits. Colorants, additives and secondary operations of any kind may alter some or all of the properties of these materials. Flammability information included herein indicates only the potential for meeting UL listing criteria and does not necessarily mean that UL listings for any given material have been secured.